



Prowaxx™ 1456 SW

ExxonMobil Specialties, Hong Kong

石油鬆蜡。

產品說明

Prowaxx™ 1456 SW 是 Prowaxx™ 系列石油粗蜡與片狀蜡產品系列中的中高範圍熔點產品。其固態下為半透明的結晶材料，熔融時呈透明的琥珀至褐色液體。此為透過嚴格控制的製程由石油中所提煉的產物。Prowaxx™ 1456 SW 由直鏈正烷烴和支鏈異烷烴的混合物所組成。

ExxonMobil 蜡的生產與控制遵循 ExxonMobil 產品品質管理系統、EN ISO 9000 或是同等標準。

應用

Prowaxx™ 1456 SW 可用於以下應用情況，惟需遵守每個管轄區中的適用法律與法規*：

- 蜡乳液
- 蜡異構化反應原料
- 蜡混合物

* 使用者必須檢查是否符合適用法規

特性與規格

特性	標準方法(a)	典型值	最小	最大
級數		高熔點		
凝固點, °C	ASTM D938		58.0	68.0
100°C 條件下的運動黏度, mm ² /s	ASTM D445		7.0	9.0
閃火點, 克氏開杯, °C	ASTM D92		220	
石油蜡的溶劑萃取物, wt%	ASTM D3235			30

附註 1: 產品在發布時已經通過認證以符合指定的數值。實際值可能在指定測試方法確立的可重複範圍內會有所偏差。

附註 2: 基於確定是否符合規格的目的，根據 ASTM E 29 方法，應該將觀察值或計算值四捨五入至在表達限值時使用的最後有效數字中的最接近單位。

(a) 可以使用替代測試方法來替代標準測試方法對產品性質進行認證。

健康與安全

本產品健康及安全建議需遵循物質安全資料表 (MSDS) 提供的指引。有關物料安全資料表可向當地經銷部門或上網獲取

(<http://www.msds.exxonmobil.com/psims/psims.aspx>)

除非另有提及，否則此處使用的所有商標皆為 Exxon Mobil Corporation 或其子公司的商標或註冊商標。

09-2025

ExxonMobil Asia Pacific Ltd

1 HarbourFront Place

#06-00 HarbourFront Tower One

Singapore 098633

+65 6885 5000

<http://www.exxonmobil.com>

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

ExxonMobil

Exxon Mobil 

© Copyright 2003-2026 Exxon Mobil Corporation. All Rights Reserved