



MOBILCUT 140 BF

Mobil Industrial , Denmark

Boron Free Aqueous Metal Working Fluid

Product Description

Mobilcut is the trademark for Mobil Industrial lubricants line of high performance water miscible metal removal fluids. Formulated with leading edge base oils, additives, and emulsifiers, the Mobilcut series of non-chlorinated products provides dependable performance in a wide array of metal removal processes. The products are designed to work in a variety of hard and soft water qualities and offer low foam potential and long-term corrosion protection for machine and components. Low maintenance and inherently stable, Mobilcut products are designed for the modern machine shop where long service life, excellent machining performance, health and environmental concerns are important factors for increased productivity. These products are supplied in concentrated form and require mixing with water at the point of use. All Mobilcut products are free of formaldehyde release agents (FAD).

Mobilcut 140 BF is a long life, boron free, water soluble fluid making it an ideal choice for grinding and general machining application in the modern machine shop. It is formulated to provide long service life, good emulsion stability and durability while helping to increase tool life and surface finish, even in difficult machining operations. Mobilcut 140 BF is an ideal choice where excellent machining performance is required for a wide variety of materials and applications, while being easy to monitor and maintain. It can work well with very soft water (5 °dH) and the emulsion is stable in use in very hard water (up to 60 °dH).

Features and Benefits

The Mobilcut series are designed to help increase the productivity of modern machine shops by providing high performance features.

Features	Advantages and Potential Benefits
Form stable emulsions and solutions	Ease of use and maintenance
Long term inherent stability	Increases batch life and reduces unpleasant odors
Low foaming potential	Improved performance even in high pressure systems
Resists formation of sticky residues	Improves machine cleanliness
High degree of corrosion protection	Reduces machine maintenance and rework of materials
Good separability from fines	Improves filterability and surface finish
Wide Range of applicability	Potential to consolidate products and reduce inventories
Compatible with high performance Mobil Vactra Oil No slideway lubricants	Easy separation and removal of tramp oil
Neutral Odor	Enhances the workplace environment
Boron free	For Regulatory compliance

Applications

Mobilcut 140 BF: Grinding and machining of cast iron and for a wide variety of materials in moderate to heavy duty operations such as milling, turning, sawing, boring, drilling and reaming where the lubricity of a soluble oil is desired.

Fluid type is micro emulsion. Mineral oil content is typically 30%. Water hardness range is from 5 to 30 °dH. Its typical refractometer factor is 1.3, due to production tolerances this value might vary slightly.

Recommended concentrations for typical operations:

Cylindrical & Surface grinding: 5-7%

Low alloy steels - milling, turning: 6-8%

Carbon alloy steels, difficult machining: 8-12%

Aluminum machining: 8-10%

Properties and Specifications

Property	
Grade	N/A
Kinematic Viscosity 20 C, mm ² /S, ASTM D7042	120
pH-Value 5.0% in 20 deg dH Water, DIN 51369	10.1
Density 15 C, kg/m ³ , DIN EN ISO12185	986
Appearance, AA.Lab.101	yellow, turbid
Appearance, 5.0% in 20 deg dH Water, AA.Lab.101	translucent

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

05-2024

ExxonMobil Nordic

Affiliate of ExxonMobil Nordic AS, Norway

Gydevang 39-41

DK-3450 Alleroed, Denmark

Tel: +45 45 99 02 10

Fax : +45 45 99 02 80

www.exxonmobil.no

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

ExxonMobil

Exxon

Mobil



© Copyright 2003-2025 Exxon Mobil Corporation. All Rights Reserved